

POLYSAFE™ VERONA PUR - PURE COLOURS

Carborundem-free, design-oriented PUR safety floor covering for areas with higher slip resistance requirements. Typical areas of application: hospital wards, clinics, nursing homes, classrooms, washrooms, WCs, serving areas, kitchens, eating areas and canteens.

Characteristics	Standards	Unit	POLYSAFE™ VERONA PUR - PURE COLOURS
Type of floor covering	EN 13845		PVC covering with particle-based increased slip resistance
Surface treatment			PUR
Description			 non-directional, with chips
Special characteristics			 safety flooring tone-in-tone slip-resistant particles
Total weight	EN ISO 23997	g/m ²	2600
Use Area	EN ISO 10874		 23  34  43
Gauge	EN ISO 24346	mm	 2,0
Packaging roll size	EN ISO 24341	m / m ²	 2 m x 20 m / 40 m ²
Residual indentation	EN ISO 24343-1	mm	≤ 0,10
Light Fastness	EN ISO 105-B02	level	≥ 6
Behaviour to fire	EN 13501-1		B _{fl} - s1
Slip resistance	EN 13845 DIN EN 16165 Ann. B		ESf R11
Pendulum test – to check the flooring for slip			 45+ wet test - 4S Rubber/ Slider 96
Impact sound reduction	EN ISO 10140-3	dB	2
Static electrical propensity	EN 1815	kV	≤ 2,0 antistatic
Bacterial Resistance	ISO 846 Part C		does not favour growth
Resistance to chemicals	EN ISO 26987		*
Binder Content	EN 13845		50.000 cycles
Castor chair	ISO 4918		yes, type W, EN 12529
Underfloor heating	EN 1264-2		suitable, max. 27 °C
VOC emissions	Indoor Air Comfort® GOLD FloorScore® Finnish M1 Classification AgBB VOC test		Eurofins certified product certified below quantifiable levels
CE	EN 14041		 B _{fl} -s1  ES  NA  DL  PCP



100% RECYCLABLE
CONTAINS RECYCLED MATERIAL



* Assignment requires labels
Sauf pour le contenu régional
except for regional content
behaviour genocyticide without



All POLYFLOR commercial
sheet vinyl ranges provide
a continuous, impervious
and hygienic flooring
solution which can be
confidently cleaned in
accordance with recom-
mended maintenance
procedures and approved
maintenance products.
The implementation of an
effective cleaning regime
is the most important
defence against infection.

*
Resistant depending on
concentration and time
of exposure, in case of
increased impact of oils,
grease, acids, alkalis and
other aggressive chemicals –
please contact us.

Subject to change due
to further technical
development.